

## INSTALLATION INSTRUCTIONS

- 4 To install an additional roll of Wall Drain, overlap the bottom edge of top roll onto the flange of bottom roll.
- 5 Fasten to wall through the Wall Drain (core only) every 12 inches. Cover the overlap area with the excess fabric on the bottom edge of top roll and secure with tape or spray adhesive.
- 6 Tuck fabric behind core on top edge of top roll and fasten to wall every 12 inches.

### Terminating Roll End

- 1 When terminating an edge of the Wall Drain, cut and remove 3 inches of core (do not cut the fabric) and tuck excess fabric behind core.

- 2 Fasten to wall vertically every 18 inches.
- 3 When finished, ensure that no exposed areas of the Wall Drain core are visible.

### Connecting Roll Ends (when adding additional lengths)

- 1 Cut and remove 4 inches of the core only from roll being added, leaving a 4 inch fabric flap.
- 2 Butt the core of the cut end against the core of previously installed roll end.
- 3 Fasten vertical edge through core only every 18 inches.
- 4 Fold 4 inch fabric flap onto the previously installed roll and secure with tape or spray adhesive.

## SPECIFICATIONS

Physical Properties	Value	Test Method
<b>Fabric</b>		
Material	Polypropylene	
Grab Tensile Strength	110 lbs.	ASTM D4632
Puncture Strength	65 lbs.	ASTM D4833
Trapezoidal Tear	50 lbs.	ASTM D4533
Mullen Burst Strength	215 psi	ASTM D3786
Elongation	60%	ASTM D4632
EOS (AOS)	100 sieve	ASTM D4751
Permittivity	3 sec <sup>2</sup>	ASTM D4491
Permeability	0.12 in/sec	ASTM D4491
Flow Rate	150 gal/min/ft <sup>2</sup>	ASTM D4491
UV Resistance (After 500 hours)	70%	ASTM D4355
<b>CORE</b>		
Material	Polystyrene	
Thickness	0.25 inch	
Compressive Strength	5,100 lbs/ft <sup>2</sup>	ASTM D1621 (Mod.)
<b>PRODUCT</b>		
Flow capacity/unit width (hydraulic gradient =.1, loading 25 psi)	9 gal/min/ft	ASTM D4716
Unrestricted In-flow Area	85%	

**DrainStar®**  
**Wall Drain 200**

**TREMCO**  
Barrier Solutions

800-876-5624 614-322-4420  
6402 East Main Street  
Reynoldsburg, OH 43068

NOTE: All information and specifications are based on the latest product information available at the time of printing. Constant improvement and engineering process make it necessary that we reserve the right to make changes without notice. All physical properties are typical values. Standard variations in mechanical properties of 10% and in hydraulic properties of 20% are normal.

©2009 Tremco Barrier Solutions, Inc. DrainStar is a registered trademark of Tremco Barrier Solutions, Inc.

Rev. 02/17 TBP-000